


## TECHINAL DATA SHEET



<b>MATERIAL</b>	<b>LDPE RECYCLED</b>
<b>FORM</b>	<b>PELLETS</b>
<b>COLOUR</b>	<b>HONEY</b>
<b>INPUT</b>	<b>GREENHOUSE AG-FILM</b>

<b>TEST</b>	<b>VALUE</b>	<b>UNIT</b>
<b>DENSITY</b>	<b>0.944 ± 0.003</b>	<b>g/cm3</b>
<b>MIFI (190°C;2.160)</b>	<b>0.882 ± 0.02</b>	<b>g/l0min</b>
<b>ASH CONTENT</b>	<b>1.01</b>	<b>%</b>
<b>TENSILE STRENGHT</b>	<b>11,88</b>	<b>(Mpa)</b>
<b>ELONGATION AT BREAK</b>	<b>469.08</b>	<b>%</b>

**Ldpe particles other tan granules = absent**

**Extruder filter = 110 mesh**

**Storage and handling: the material is supplied in 1000-1200 kg big bags. Other presentations are possible upon request. It is advisable to store in a ventilated and dry place, protected from light and weather impacts.**

All information in this datasheet is provided in good faith and is based on our current knowledge and experience. The data above represent typical values and should not be construed as guaranteed specifications. It is the buyer responsibility to determine the suitability of the product under the actual conditions of intended application.