

Paraje El Bermejo s/n. - 04110 CAMPOHERMOSO (Nijar). Móviles: 610 720 642 - 610 720 643 jmlopezv@recicladosnijar.com / www.recicladosnijar.com

TECHINAL DATA SHEET







MATERIAL		
FORM	PELLETS	
COLOUR	HONEY	
INPUT	GREENHOUSE AG-FILM	

TEST	VALUE	<u>UNIT</u>
DENSITY	0.944 ± 0.003	g/cm3
MIFI (190ºC;2.160)	$\boldsymbol{0.882 \pm 0.02}$	g/l0min
ASH CONTENT	1.01	%
TENSILE STRENGHT	11,88	(Mpa)
ELONGATION AT BREAK	469.08	%

Ldpe particles other tan granules = absent Extruder filter = 110 mesh

Storage and handling: the material is supplied in 1000-1200 kg big bags. Other presentations are possible upon request. It is advisable to store in a ventilated and dry place, protected from lightand weather impacts.

Ali information in this datasheet is provided in good faith and is based on our current knowledge and experience. The data above represent typical values and should not be construed as guaranteed specifications. It is the buyer responsibility to determine the suitability of the product under the actual conditions of intended application.